

CABLE GROUT

Product Codes

TG108, Packaging listed overleaf.

Description

Cable Grout is a specially formulated Portland cement powder mix designed for the grouting of cables in post-tensioned concrete for EN 446(2007) and CARES Appendix PT10 procedures.

The mix design consists of a blend of fine and ultra fine cements plus a set of synergistic admixtures. The grout powder is packaged in 20kg durable, moisture resistant bags ready for on site mixing.

The material readily mixes with water to produce a particularly fluid flowing grout which will penetrate and fill fine voids within and around the cables then harden without shrinking to give a high strength product.

Particular advantages of the product include quick and easy mixing with water producing a flowing mix which promotes penetration into confined spaces. The grout is shrinkage compensated and contains a powerful corrosion inhibitor to protect the cables.

Once hardened and cured, high compressive strengths are achieved giving resistance to static and dynamic stresses. Cable Grout has a total chloride, sulphate and sulphide-ion content below that specified in EN 447 and CARES PT10.

Uses include: Grouting of cable ducts, voids

and fine fissures.
Support of cable anchor plates and ground anchors.
To provide bearing or contact between structural elements.
Grouting behind shafts and tunnel linings.
Underpinning, loose floor and road slabs.

Standards

Cable Grout has been tested in accordance with the appropriate parts of the following Standards: EN445, EN446, EN447, EN196-1, EN196-3.

CARES PT10 certificate number 080706 (copies available on request).

Specification Outline

Grouting works shall be carried out using Cable Grout as manufactured by Tecroc Products Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Tecroc Products Ltd is CARES certified for the production and supply of pre-bagged grout material to appendix PT10 for use in post-tensioning systems.

Typical Grout Properties @ 20 °C

Water content by weight 33% minimum to 35% maximum (6.6 to 7 litres per 20kg bag).

Compressive Strength Tested To EN 196-1 (W/P 0.35)

1 Day	3 Days	7 Days	28 Days
18N/mm ²	40N/mm ²	55N/mm ²	65N/mm ²

Typical results from EN445 testing at 33% water content.

Test type	Result specified in EN 447:2007 & PT10	Result obtained by testing Cable Grout
2mm sieve test	No lumps	No lumps
Flow cone	T ₀ <25s T ₃₀ <25s and within 20% of T ₀	T ₀ 14.5s T _{30A} 14.3s T _{30B} 13.8s
Bleeding	Bleeding 0.3% max	Bleeding 0.1%
Volume change	Volume change - 1 to 5% max	Volume change -0.27%
Compressive strength test	> 27 N/mm ² @ 7 days	84.5 N/mm ² @ 7 days
Initial and final setting test (EN196-3)	Initial > 3 hours Final < 24 hours	Initial > 6 hours. Final < 22 hours

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

CABLE GROUT

Instructions For Use

Preparation

All necessary preparatory work must be completed before the grout is mixed. The fluid nature of the grout at 35% maximum water to powder ratio enables it to flow long distances in well prepared elements. Sufficient head should always be provided by positive pump pressure to ensure grout flow along or upwards in the cable ducts. Site trials may be carried out to confirm that suitable equipment is available and an appropriate water / powder ratio is chosen. A surcharge stand pipe should be allowed for to take up 'sinkage' as the grout fills voids. Ensure that enough grout is mixed and available for the grouting operation to be completed in one continuous pour.

Mixing

For each 20kg bag of Cable Grout, a maximum of 7 litres of water are required. For single bag mixes suitable mixing may be achieved using a high torque slow speed drill with a Grout Stirrer. For larger mixes use a standard grout mixer such as the Groutmaster, Putzmeister or Colcrete series.

Pour the required quantity of clean water into the mixing vessel. Slowly add the Cable Grout to the water whilst continually mixing. Keep the mixed grout in a slow agitating holding tank prior to placing.

Placing

Where Cable Grout will be pumped into place the grout pump should be of the positive displacement type capable of generating at least 10 bars pressure. Up to 40 bars may be required to fill particularly long or high upward running ducts. The rate and continuity of placing should be controlled to encourage good penetration of grout into the voids within the duct and the expulsion of air from the duct. Do not disturb once grouting has been completed before the grout has hardened. Cable Grout may be placed at temperatures between 5°C and 35°C. For placing temperatures outside this range contact the Technical Service Department.

Curing

After grouting has been completed, or when the formwork is removed, any exposed grout must be cured immediately with Polycure at the rate of 10m²/litre. During adverse weather conditions, such as high temperatures and drying winds, a second application of Polycure should be applied after the first application is dry.

Precautions**Health and Safety**

Cable Grout is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice.

Full health and safety data are given in Product Safety Data Sheet.

Fire

Cable Grout is non-flammable

Yield

Each 20kg bag of Cable Grout will yield approximately 13 litres of mixed material at water dose rate of 35%.

Storage And Shelf Life

Cable Grout will have a storage life of 6 months in unopened bags when kept in dry conditions at a temperature between 5°C and 35°C. Storage at higher temperatures and high humidity may reduce shelf life.

Packaging And Ordering

Cable Grout is supplied:

20kg valvesack bags Product Code TG108

For further information and sales please contact your local Tecroc Products office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering