

TECHNICAL DATA

Revision Date 01/2008

THIXOTROPIC JOINT FILLER (TJF)

Product Codes

TP48, Packaging listed overleaf

Description

TJF is a Portland cement based powder mix including special thixotropic and shrinkage compensating components. The product mix design requires a low water addition to produce a high strength mortar designed for structural support.

TJF is pump placed and will produce in situ structural fill and support. Once placed TJF will stay without shuttering or pointing when pumping pressure is relieved. The thixotropic "stay" characteristic will resist hydrostatic pressure within the joints being filled. TJF can be used for placing in horizontal and vertical gaps of 5mm to 100mm where a cementitious mortar infill is required and flow grouting is inappropriate. TJF is pre-packaged ready for on site mixing only requiring addition of the measured volume of water. The product may be mixed using the drill and paddle technique followed by hand or mechanical pump placement or for larger jobs mixer pumps can be used. TJF is chloride free and can be safely used in contact with steel reinforcement.

Uses include: Structural support between and beneath precast concrete elements
Permanent insitu shuttering in joints between precast concrete elements which will be post grouted.
Rapid placement using Duo-Pump systems.

Specification Outline

Placing of mortar for structural fill and support shall be carried out using Thixotropic Joint Filler as manufactured by Tecroc Products Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Typical Properties @ 20°C

Compressive strength

Water addition:

4.0 Litres per 25 kg bag of Thixotropic Joint Filler

Age at Test	1 Day	7 Days	28 Days
	20N/mm ²	40N/mm ²	55N/mm ²

Density 2100 kg/m³

Setting Times

Initial 210 minutes Final 240 minutes

Standards

TJF has been tested in accordance with appropriate parts of the following standard: B.S. 1881



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

TECHNICAL DATA

Revision Date 01/2008

THIXOTROPIC
JOINT FILLER
(TJF)**Instructions For Use****Preparation**

Contact surfaces should be sound and clean. Remove all loose material, heavy mill scale and oily deposits.

Priming

The prepared surfaces should be pre-dampened. Remove any standing water before placing the TJF mortar.

Mixing

TJF is supplied in 25kg bags. The water requirement to produce the mortar is 4.0 to 4.5 litres of water

Mixing Prior to Pumping

Pour the required quantity of water into a suitable mixing vessel. Slowly add the powder to the water whilst continuously mixing. Mechanical mixing is recommended. Suitable mixers include a slow speed high torque drill with a Mortar Stirrer or a forced action mixer such as Creteangle.

"Duo Mix" Mixing

Mixer pumps, such as the Duo Mix will mix the TJF on the pump unit prior to pumping into place. Load the TJF into the mixer-pump in accordance with the equipment manufacturer's instructions.

Application

Hand mixed mortar should be loaded into a suitable pump unit and placed in accordance with the pump supplier's instructions. Duo Mix units will allow the mortar to be mixed and placed continuously from the single unit. Pumping rates of some 12 to 15 litres per minute have been found to be satisfactory. At these rates the build up of hydrostatic pressure in vertical joints will not cause the grout to flow from openings in the jointing area.

Ensure complete filling of the gap and then finish the exposed surface with a dampened steel trowel.

Curing

TJF may be applied at temperatures between 5°C and 35°C. In moderate ambient conditions no special curing is necessary. Under hot and high drying conditions curing of exposed surfaces should be undertaken in accordance with good concrete practice.

Precautions**Health and Safety**

TJF is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice.

Full health and safety data are given in the Product Safety Data Sheet.

Fire

TJF is non-flammable

Yield

Each 25kg bag of TJF will yield approximately 13.5 litres of mixed material.

Storage And Shelf Life

TJF will have a storage life of 6 months in unopened bags when kept in dry conditions at a temperature between 5°C and 35°C. Storage at higher temperatures or high humidity may reduce shelf life.

Packaging And Ordering

TJF is supplied in 25kg valvesack bags.

25kg valvesack bags Product Code TP48

For further information and sales please contact your local Tecroc Products office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering