

SBR MORTAR

Product codes

TP01, packaging listed overleaf.

Description

SBR Mortar is a Portland cement based two component product comprising a fibre reinforced powder mix and a modified styrene butadiene latex gauging liquid.

SBR Mortar can be used in repairs carried out vertically and overhead. The repair mortar enables a fine fair faced finish to be achieved and will give protection to exposed reinforcing steel. SBR Mortar complies with the proposed Materials for the Repair of Concrete Highway Structures BD 27/86.

Uses Include:

- Thick section repairs.
- Concrete beams & columns.
- Wall sections.
- Stone fascias.
- Balustrades.
- Blockwork.

Typical Mortar Properties @ 20°C

Compressive Strength

1 Day	7 Days	28 Days
9.0 N/mm ²	16.7 N/mm ²	22.5 N/mm ²

Density: 1380 kg/m³
 Coefficient of Thermal Expansion: 8-10 x 10⁻⁶/°C
 Useable Life: 60 minutes
 Flexural: 7.5 N/mm² @28 days
 Chloride Ion: 0.002%

Standards

SBR Mortar has been tested in accordance with the appropriate parts of the following standards: B.S. 4551

Specification Outline

Concrete repairs shall be carried out using SBR Mortar as manufactured by Tecroc Products Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Instructions For Use

Preparation

Remove all loose material, plaster, paint and oily deposits to produce a sound clean surface. Roughen smooth concrete to give a good mechanical key. Cut back repair edges to avoid feather edging. Expose reinforcing steel two thirds of its circumference in a sound concrete background. Totally expose steel in areas where concrete repairs are deeper than the steel embedment depth. Clean back corroded reinforcing steel to bright metal. Protect cleaned steel with Steel Primer.

Priming

To prime the prepared concrete surface and reinforcing steel use a slurry formed from a mix of:
 SBR Mortar powder : One part by volume
 SBR Mortar gauging liquid : One part by volume
 Mix the slurry primer in a suitable mixing vessel using a slow speed drill and Mortar Mixer. Do not mix more than can be applied within the usable time, 45 minutes at 20°C. Apply mortar before the priming coat has dried.

Mixing

SBR Mortar is supplied as 17.5kg of powder mix and 5 litres of gauging liquid. The mixing proportions to produce rendering and repair mortar are:
 Rendering 4.75 parts by volume powder
 to 1.0 part by volume gauging liquid
 Repair Mortar 6.00 parts by volume powder
 to 1.0 part by volume gauging liquid

Pour the gauging liquid into a suitable mixing vessel and slowly add the powder to the liquid whilst continuously mixing. Mix using either a slow speed drill with a Mortar Mixer or a forced action mixer such as Cretangle or Pennine. Continue mixing for three minutes after all the powder has been added.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Head Office
 Holly Lane Industrial Estate
 Atherstone
 Warwickshire
 CV9 2RN
 Tel: 01827 711755
 Fax: 01827 711330

Irish Distributor
 Construction Chemical Supplies
 Unit 219
 JFK Road JFK Industrial Est
 Dublin 12
 Tel: 00 353 1 450 3896
 Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

SBR MORTAR

Instructions For Use

Placing

Apply the SBR Mortar firmly into the repair area. It may be necessary to use a gloved hand to place and compact the mortar behind reinforcing steel and into narrow corners and edges. Initially finish the surface with a wooden/plastic trowel. Allow the mortar to stiffen then finish finally with a dampened steel trowel.

Application thickness may range from 10mm to 50mm in a single layer vertically and 10mm to 30mm overhead. In situations where thicker layers are required to be built up, the surface of the under layer should be left with a wood float finish and should be scored. Subsequent primer and mortar layers may be applied as soon as the initial layer is firm enough not to distort under the new work.

SBR Mortar may be applied at temperatures between 5°C and 45°C. For application at temperatures outside this range contact The Technical Service Department.

Curing

Curing should be undertaken in accordance with good concrete practice. The curing regime should be applied as soon as finishing is complete. For large areas, as each half square metre is completed curing should be started. Suitable methods of curing include water spray, polythene sheeting and spray applied concrete curing membrane.

Precautions

Health and Safety

SBR Mortar is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice.

Full health and safety data is given in Product Safety Data Sheet.

Fire

SBR Mortar is non-flammable

Yield

SBR Mortar powder is packed in 22.5kg combined units each unit will yield is approximately 14.0 litres of mixed material.

Storage And Shelf Life

SBR Mortar will have a shelf life of 6 months when kept in dry conditions at a temperature of 5°C to 45°C. Storage at higher temperatures and high humidity may reduce the shelf life.

Packaging And Ordering

SBR Mortar is supplied in:
22.5kg Combined Units Product Code TP01

For further information and sales please contact your local Tecroc Products office as listed below.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk