

FASTSET CONCRETE

Product Codes

DH57 Summer grade, DH123 Winter grade, DH 138 Winter Fine grade. Packaging listed overleaf.

Description

Fastset Concrete is a single pre-mixed Portland cement based non-shrink concrete suitable for thick section placing where rapid early strength gain is required.

Fastset Concrete may be used for the support of road ironwork and highway furniture, barriers and stanchion posts. The mixed concrete, when placed, will harden in approximately 10 minutes. The compressive strength gain will reach 20N/mm² within 2 hours allowing early opening of roads to vehicular traffic.

The self-contained product only needs to be mixed with water on site and the rapid setting assists the re-bedding of road ironwork and the setting in of new systems. The product is chloride free and can be safely used with cast iron and steel units. The concrete can be placed in sections of 20mm to 200mm in thickness for standard grade or 10 to 100mm for fine grade. Greater thicknesses can be built up in layers. After placement no special curing is required in moderate ambient conditions.

Fastset Concrete is available in Summer and Winter grades for use all year round.

Uses include: Installation of road ironwork.

Support of road furniture.

Placing of stanchion posts.

Roadway rapid repairs.

Typical Concrete Properties

Compressive Strength

Water addition: 2.75 litres per 25kg of Fastset Concrete Summer grade @ 20°C and Winter grade @ 10°C

2 Hour	1 Day	7 Days	28 Days
22 N/mm ²	35 N/mm ²	45 N/mm ²	55 N/mm ²

Variations in water content and ambient temperature for particular applications may alter concrete consistency and compressive strength achieved.

Density 2250 kg/m³.

Coefficient of Thermal Expansion 11 x 10⁻⁶/°C

Specification Outline

Bedding and support sections shall be carried out using Fastset Concrete as manufactured by Tecroc Products Ltd. The product must be stored, handled and placed strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Standards

Fastset Concrete has been tested in accordance with appropriate parts of EN 12390.

Instructions For Use

Preparation

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. The work area should be pre-wetted taking care to remove any standing water before placing the Fastset Concrete.

Mixing

To achieve the most consistent concrete mix, mechanical mixing is recommended. If hand mixing care should be taken to ensure that the mix is fully wetted out without the use of excess water. Mechanical mixing may be carried out in a suitable vessel using a slow speed high torque drill and Concrete Stirrer. Thorough hand mixing may be carried out using a clean spot board or wheelbarrow. Each 25kg bag of Fastset Concrete requires 2.5 to 3.0 litres of water to give a medium workability concrete consistency. Excess water should not be added. Once setting of the concrete has commenced, further mixing should not be used to re-work the mix.

The concrete should be placed within approximately 10 minutes of mixing. The working time may be extended in cold ambient conditions and may be slightly shortened in hot ambient conditions. For cold weather working warm mixing water at up to 30°C may be used (summer grade only).

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

TECROC
PRODUCTS



Grouts



Structural Support
Mortars



Concrete Repair
Products



Construction
Adhesives



Resin Et
Cementitious
Anchors



Highway
Products



Coatings



Waterproofing



Ground
Engineering

FASTSET CONCRETE

Instructions For Use

Placing

Mixed Fastset Concrete should be placed onto the dampened prepared surface as soon as mixing is complete. Once placed fully compact the concrete to obtain maximum strength development. The bed thickness applied in a single application should be between 20mm to 200mm for standard grade or 10 to 100mm for fine grade. Thicker support beds can be achieved by applying further material as soon as the lower bed has hardened sufficiently not to distort under the additional work.

The placed concrete will have hardened sufficiently to carry out further work within some 20 minutes depending on the surrounding ambient conditions and the grade being applied.

Curing

No special curing is required at temperatures between 5°C and 35°C. For placing at temperatures outside this range contact the Technical Service Department.

Precautions

Health and Safety

Fastset Concrete is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice.

Full health and safety details are given in Product Safety Data Sheet.

Fire

Fastset Concrete is non-flammable

Yield

The volume yield of each 25kg bag of Fastset Concrete is approximately 12 litres.

STORAGE AND SHELF LIFE

Fastset Concrete will have a shelf life of 6 months when kept unopened, clear of the ground, in dry conditions, protected from excessive draught, between temperatures of 5°C and 35°C. Storage at higher temperatures and high humidity may reduce the shelf life.

PACKAGING AND ORDERING

Fastset Concrete is supplied in 25kg bags:

Summer grade	Product Code DH57
Winter grade	Product Code DH123
Winter Fine grade	Product Code DH 138

For further information and sales please contact your local TECROC Products office as listed below.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

TECROC
PRODUCTS