

HIGHWAY FAST PATCH

Product Codes

DH08, Packaging listed overleaf

Description

Highway Fast Patch is a two component product supplied as a pre-mixed Portland cement based non-shrink powder component plus a co-polymer latex gauging liquid.

Highway Fast Patch can be used for repairs where rapid access and usage is required. The repair mortar enables a fair faced finish to be achieved and will give protection to exposed reinforcing steel.

Working time is approximately 20 minutes and the mixed mortar, when placed, will harden in approximately 10 minutes. The compressive strength gain will reach 10N/mm² within 1 hour allowing for foot traffic. In areas for use with vehicular traffic the opening strength of 20N/mm² will be typically obtained within 4 hours.

The product is chloride free and can be safely used in contact with reinforcing steel. The mortar can be placed in sections of 10mm to 100mm in thickness. After placement no special curing is required in moderate ambient conditions.

Uses Include:

Surface and section repairs to:
Kerbs
Road surfaces
Pathways
Concrete plinths
Concrete and stone blockwork

Typical Mortar Properties @ 20°C

Compressive Strength

1 Hour	2 Hours	4 Hours
10N/mm ²	16N/mm ²	20N/mm ²

1 Day	7 Days	28 Days
32N/mm ²	40N/mm ²	50N/mm ²

Density 2000 kg/m³

Coefficient of Thermal Expansion 8-10 x 10⁻⁶/°C

Useable Life 20 minutes

Standards

Highway Fast Patch has been tested in accordance with the appropriate parts of BS 4551

Specification Outline

Concrete repairs shall be carried out using Highway Fast Patch as manufactured by Tecroc Products Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Instructions For Use

Preparation

Remove all loose material, plaster, paint and oily deposits to produce a sound clean surface. Roughen smooth concrete to give a good mechanical key. Cut back repair edges to avoid feather edging. Clean back corroded reinforcing steel to bright metal. Protect cleaned steel with Steel Primer.

Priming

Prime the prepared concrete surface using part of the Highway Fast Patch gauging liquid as supplied. Allow the primer coat to become tacky, approximately 20 minutes at 20°C. Apply mortar before the priming coat has dried.

Mixing

Pour the remaining gauging liquid into a suitable mixing vessel and slowly add the powder to the liquid whilst continuously mixing. A small amount of water may be added to adjust the mortar workability. Mix using either a slow speed drill with a Mortar Stirrer or a forced action mixer such as the Creteangle. Continue mixing until the mortar produced is of an even colour.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

TECHNICAL DATA

Revision Date 01/2008

HIGHWAY
FAST PATCH

Precautions

Health and Safety

Highway Fast Patch is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs wash thoroughly with clean water. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice.

Full health and safety data are given in Product Safety Data Sheet.

Fire

Highway Fast Patch is non-flammable

Yield

Highway Fast Patch powder is packed in 10kg combined units. Each unit will yield approximately 5 litres of mixed material.

Storage And Shelf Life

Highway Fast Patch will have a shelf life of 6 months when kept in dry conditions at a temperature of 5°C to 45°C. Storage at higher temperatures or high humidity may reduce the shelf life.

Packaging And Ordering

Highway Fast Patch is supplied in 10kg combined units.

10kg combined unit Product Code: DH08

Steel Primer is supplied in:

20kg Bags Product Code: ACR01

For further information and sales please contact your local Tecroc Products Office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering