

FRAMEFIX MORTAR SUMMER - WINTER

Product Codes

DH06s, DH06w Packaging listed overleaf.

Description

Framefix Mortar is polyester resin based material used for the bedding and levelling of all types of frames in vehicular road surfaces. The product is supplied as a two pack system ready for on site mixing consisting of two tins of base resin and two bags of catalysed filler. The mixed mortar will harden to give rapid strength gain reaching 52N/mm₂ in 1 hour allowing road opening to vehicular traffic within 3/4 to 1 hour. The placed frames will resist compressive and high impact loads. The chemical mechanism will continue at temperatures down to 0°C with only a small increase in hardening time. The hardened mortar is resistant to chemical attack from petroleum products and road salt.

Two grades, Summer and Winter, are available.

Framefix Mortar complies with Highways Agency Advice Note 104/02 Design Manual for Roads and Bridges – Chamber Tops and Gully Tops for Road Drainage and Services: Installation and Maintenance.

- Uses include:**
- Re-bedding of raised manholes
 - Support of road furniture
 - Bedding of frames in new roads
 - Most rapid opening of newly placed frames and road furniture

Typical Mortar Properties @ 20°C

Working Time @ 20°

Framefix Mortar Winter Grade: 8 - 12 minutes
(above 20°C setting will be rapid)

Framefix Mortar Summer Grade : 18 - 22 minutes
(below 10°C setting will be extended)

Compressive Strength

Mortar Mix By Volume

Resin 1 part, Catalysed Filler 3³/₄ parts

1 Hour	2 hours	1 Day
52N/mm ₂	64N/mm ₂	75N/mm ₂

Density	2000kg/m ³
Flexural Strength @ 2 Hours	21N/mm ₂
Tensile Strength @ 2 Hours	7.5N/mm ₂
Compressive Modulus	15kN/mm ₂

Specification Outline

Bedding of frames shall be carried out using Framefix Mortar as manufactured by Tecroc Products Ltd. The product must be stored, handled and placed strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Standards

Framefix Mortar has been tested in accordance with the relevant parts of BS 6319, HA104/02

Instructions For Use

Preparation

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. Any loose brickwork should be re-bedded using a slightly resin rich mortar mix.

Mixing

To achieve the most consistent mortar mix, mechanical mixing is recommended. Hand mixing is suitable for small mixes but care should be taken to ensure that the mix is fully wetted out with resin. Mixing may be carried out in the plastic package pail or a similar suitable mixing vessel. Suitable mixers include a slow speed high torque drill and Mortar Stirrer. For full pack mixing of Frame Fix Mortar pour all of the resin contained in the two tins within the pack into the mixing pail. Slowly add the catalysed filler while continually mixing. Continue mixing after all the catalysed filler has been added until the mix is powder free and uniform. The chemical reaction of setting is rapid. The mixed mortar should be placed immediately after mixing. The working time may be extended in cold ambient conditions and may be shortened in hot ambient conditions.



Grouts



Structural Support Mortars



Concrete Repair Products



Construction Adhesives



Resin Et Cementitious Anchors



Highway Products



Coatings



Waterproofing



Ground Engineering

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk

FRAMEFIX MORTAR

SUMMER - WINTER

Instructions For Use

Placing

Set suitable levelling shims onto the working surface ready to receive the frame or unit. Place the mixed mortar onto the prepared surface and lower the frame or unit onto the mortar and knock down onto the pre-set shims to line and level. The bed thickness applied in a single application should be between 10mm to 50mm. Thicker support beds can be achieved by applying further material as soon as the lower bed has hardened sufficiently not to distort under the additional work. The placed mortar will have hardened sufficiently to carry out further work, such as haunching, within 20 to 30 minutes depending on the surrounding ambient conditions and product grade. Clean tools with Solvent before mortar has started to harden.

Curing

No special curing is required at temperatures between 5°C and 35°C. For placing temperatures outside this range contact the Technical Service Department.

Precautions

Health and Safety

Framefix Mortar is a resin based product. Resins and solvents may cause allergic reactions in some people. Wear gloves, use barrier cream on unprotected skin areas and wear eye protection when mixing, using and cleaning. Ensure adequate ventilation to prevent inhalation of vapours. If skin contact occurs remove resin immediately with cleansing cream and wash with soap and water. Do not use solvent. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice. If swallowed do not induce vomiting. Seek medical advice immediately.

Full health and safety data are given in Product Safety Data Sheet.

Fire

Should fire occur extinguish with CO₂ or foam.

Yield

The volume yield of each 25kg pack of Framefix Mortar is approximately 12.5 litres of mixed mortar.

Storage And Shelf Life

Framefix Mortar will have a shelf life of 6 months in unopened containers when kept in dry conditions at a temperature of 5°C to 25°C. Storage at higher temperatures and high humidity may reduce shelf life.

Packaging And Ordering

Framefix Mortar is supplied in 25kg packs.
 25kg packs (summer grade) Product Code DH 06s
 25kg packs (winter grade) Product Code DH 06w
 Solvent is supplied in 5 litre and 1 litre tins.
 5 litre tins Product Code TM02
 1 litre tins Product Code TM08

For further information and sales please contact your local Tecroc Products Office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering

Head Office
 Holly Lane Industrial Estate
 Atherstone
 Warwickshire
 CV9 2RN
 Tel: 01827 711755
 Fax: 01827 711330

Irish Distributor
 Construction Chemical Supplies
 Unit 219
 JFK Road JFK Industrial Est
 Dublin 12
 Tel: 00 353 1 450 3896
 Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk