

HIGH BUILD PROTECTIVE COATING

Product codes

TM40, TM41, packaging listed overleaf

Description

High Build Protective Coating is a two part solvent free epoxy resin product consisting of a pigmented base resin component plus a pale yellow hardener component. The colour coding enables homogeneous mixing to be easily achieved. The product is applied as a high build protective coating to steel, concrete and other construction materials. Applied coatings are resistant to mechanical damage, abrasion and will give protection against weathering and chemical attack. The product gives a high build coating in a single application which cures to hard semi-gloss finish within 24 hours. Grey and black colours are available.

Uses include: Steel fabrications and reinforcements
Floors, walls and soffits.
Marine and sewage works.
Warehouse storage areas plus industrial factory areas.
Exposed reinforcing strand ends.
Exposed reinforcing steel ends.

Typical Properties @ 20°C

Specific Gravity:	1.65
Useable Life:	45 Minutes
Tack Free:	6 Hours
Dry Film Thickness:	300 Microns in one coat
Initial Usage:	24 Hours

Specification Outline

Protective coating shall be carried out using High Build Protective Coating as manufactured by Tecroc Products Ltd. The product must be stored, handled and used strictly in accordance with the manufacturer's instructions.

Quality Assurance

Tecroc Products Ltd is a firm of Assessed Capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by SGS Ltd Systems and Services Certification.

Instructions For Use

Preparation

All contact surfaces must be sound, clean, dry and provide a good mechanical key. For steel surfaces rust, millscale or any other impurities should be removed bringing the surface to a bright metal condition. For concrete surfaces remove all loose material, paint, plaster and oily deposits. For best results light grit blasting is recommended.

Priming

No special priming is required.

Mixing

The High Build Protective Coating base resin component is supplied in a container which is large enough to receive the hardener component and act as the mixing vessel. Pour all of the hardener component into the base container and mix using a slow speed high torque drill with a Mortar Stirrer. Mixing should be continued for two minutes to achieve a uniform consistency and colour.



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Web site: www.tecroc.co.uk

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

E-mail: enquiries@tecroc.co.uk

HIGH BUILD PROTECTIVE COATING

Instructions For Use

Coating

Apply the High Build Protective Coating as a single thick coat using a stiff bristle brush. Do not attempt to brush out the applied material. The applied thickness of 300 microns may be monitored using a simple thickness gauge to check the application during the work.

All tools and equipment should be cleaned with Solvent. Hardened High Build Protective Coating may only be removed mechanically.

High Build Protective Coating may be applied at temperatures between 10°C and 35°C. For applications outside this range contact the Technical Service Department.

Curing

Typical curing times at 20°C

Initial usage : 24 Hours
Full cure : 7 Days

PRECAUTIONS

Health and Safety

High Build Protective Coating is a resin based product. Resins and solvents may cause allergic reactions in some people. Wear gloves, use barrier cream on unprotected skin areas and wear eye protection when mixing, using and cleaning. Ensure adequate ventilation to prevent inhalation of vapours. If skin contact occurs remove resin immediately with cleansing cream and wash with soap and water. Do not use Solvent. Should eye contact occur rinse immediately with plenty of clean water and seek medical advice. If swallowed do not induce vomiting. Seek medical advice immediately.

Full health and safety data are given in Product Safety Data Sheet.

Fire

High Build Protective Coating is classified as non-flammable.

Solvent is flammable.

Should fire occur extinguish with CO₂ or foam.

Yield

High Build Protective Coating is packed in 1.65kg combined units with 8 units in an outer box. From each 1.65kg unit the yield is approximately 1litre of mixed material. Coverage is approximately 3.3m² litre.

Storage And Shelf Life

High Build Protective Coating will have a shelf life of 12 months when kept in dry conditions at a temperature of 5°C to 45°C. Storage at higher temperatures and high humidity may reduce the shelf life.

PACKAGING AND ORDERING

High Build Protective Coating is supplied in:
1.65kg Combined Units Product Code Black TM40
Grey TM41

Solvent is supplied in:

5 Litre cans	Product Code	TM2
1 Litre cans	Product Code	TM8

For further information and sales please contact your local Tecroc Products office as listed below.

Tecroc Products Ltd products are guaranteed against defective materials and manufacture. Products are sold subject to the Tecroc Products Ltd Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. Tecroc Products Ltd endeavours to ensure that the above data and any further advice is correct, however, it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control.

Head Office
Holly Lane Industrial Estate
Atherstone
Warwickshire
CV9 2RN
Tel: 01827 711755
Fax: 01827 711330

Irish Distributor
Construction Chemical Supplies
Unit 219
JFK Road JFK Industrial Est
Dublin 12
Tel: 00 353 1 450 3896
Fax: 00 353 1 450 3298

Web site: www.tecroc.co.uk

E-mail: enquiries@tecroc.co.uk



Grouts

Structural Support
MortarsConcrete Repair
ProductsConstruction
AdhesivesResin Et
Cementitious
AnchorsHighway
Products

Coatings



Waterproofing

Ground
Engineering